

# World Champion metallic effects



How can we reproduce the  
**GOLD** effects?



## METALLIC LAYER (TRANSFER APPLICATION)

800 g/l Nearprint TMPL

Brush (pure product), dry at 100°C

Apply the metallic layer (transfer paper) by pressing it at 3-4 bar, 120°C for 40". When you press use a silicone paper between the hot press and the transfer paper to avoid sticking of the paper on the steel of the press

Leave the garment for 15' (to cool after hot pressing) and remove the transfer paper; the metallic effect will remain stuck on the garment

In case of application of the glue (Nearprint TMPL) alone proceed as above and after drying Nearprint TMPL press it (without transfer paper). When you press use a silicone paper between the hot press and the garment to avoid sticking of the glue (and the garment) on the steel of the press.





**First press the garment to make wrinkles.  
Apply Nearprint TM-PL.  
Dry at 80 – 100° C.  
Condition for several hours. Apply metal foil in Gold, Silver, Copper, Petrolio – and many other effects.**

Lamina  
Metallizzata  
available in many  
different effects.

Please ask for  
details.

