

Print Discharge effects on Garments



Reactive dyes discharged with
NEARISERVE NTZ and
illuminated with pigments and
NEARPRINT 2CP

Garments must be dyed with reactive or direct dyes suitable for discharge.

Nearchimica dischargeable reactive dyes are:

Neareafix Yellow AC-3G

Neareafix Yellow AC-3R 150%

Neareafix Orange AC-4R

Neareafix Red AC-3B 150%

Neareafix Brilliant Blue AC-BRF 150%

Neareafix Navy Blue AC-BF 125%

Neareafix Black CF-VB

Neareafix Black FST powder

Neareafix Black FST liquid



Extremely complex prints are possible with the aid of a plotter.

Apply the printed design using a carousel garment printing machine



.... or by hand by brushing, spraying etc.

In the past, discharge printing would have involved complex recipes.

Nearchimica makes it easy with 2 simple components:

NEARPRINT 2CP

NEARISERVE NTZ





Add

NEARPRINT WHITE AV

for white discharge

and

NEARSTONE pigments

for illuminated effects

For example:

**1000 g NEARPRINT 2CP
200 g NEARISERVE NTZ
40 g NEARSTONE RED CBF**

**1000 g NEARPRINT 2CP
200 g NEARISERVE NTZ
200 g NEARPRINT WHITE AV**

**1000 g NEARPRINT 2CP
200 g NEARISERVE NTZ
40 g NEARSTONE
TURQUOISE AC**

Imitation discharge



An “imitation discharge” effect can be achieved by using a ready made paste, Nearcover ST with excellent covering power to prevent the underlying shade of the dyed garment from showing through the print. Examples:

1000 g Nearcover ST
40 g Nearstone
Gold Yellow TE
50 g Nearfinish TS9

1000 g Nearcover ST
40 g Nearstone
Turquoise AC
50 g Nearfinish TS9

1000 g Nearcover ST
150 g Nearprint White
AV
50 g Nearfinish TS9