



**NEARSTONE
BRX**

Neareasul

dyestuffs

Nearchimica.it



CONCENTRATION	LIGHT XENOTEST 1/1 base NEARSTONE BRX UNI EN ISO B02	LIGHT XENOTEST 1/1 base PPT UNI EN ISO B02	WASHING AT 60°C UNI EN ISO 105 C06	DOMESTIC LAUNDRING 1 g/l Sodium Perborate UNI EN ISO R105 C06	DOMESTIC LAUNDRING 0,1 g/l available Chlorine UNI EN ISO 105 C06	ALKALINE PERSPIRATION UNI EN ISO 105 E04	ACID PERSPIRATION UNI EN ISO 105 E04
----------------------	---	---	--	--	---	--	--

* 1st value = shade degradation
* 2nd value = staining on cotton
* 3rd value = staining on wool

	20%	3	4	4/5	3/4	3	5	5
Yellow E-Y liq.	20%	3	4	4/5 5 5	3/4 3 5	3 4 5	5 5 5	5 5 5
Red E-BG liq.	20%	5	5/6	4/5 4 4/5	4 4 4	3 4 4	4/5 4 5	4/5 4 5
Bordeaux E-6R liq.	20%	5	6/7	5 3/4 4	5 3 2	5 3 2	5 5 5	5 5 5
Brown E-R liq.	20%	4/5	6/7	5 5 5	3/4 3/4 3	3 3/4 3/4	5 5 5	4/5 4/5 5
Brown E-GN liq.	20%	4	4/5	4/5 5 5	2 3/4 5	2 4 5	5 5 5	5 5 5
Blue E-2G liq.	20%	4	6/7	4/5 4/5 5	3 2 2	1/2 4 5	5 5 5	5 5 5
Green E-N liq.	20%	3	5/6	4 4 4/5	3 2 3/4	2 4 5	4 4 4	4 5 5
Olive Green E-B 150% liq.	20%	5	6	4 5 5	2/3 3 5	1/2 4/5 5	5 5 5	4/5 5 5
Black E liq.	20%	5	5/6	4/5 4/5 5	3 3 3	3/4 4/5 5	5 5 5	4/5 4 4/5
Black R liq.	20%	5	6/7	4/5 5 4/5	4/5 4/5 5	1/2 4 4	4/5 4/5 4/5	4/5 4 4/5



The shades shown by the pattern cards in electronic format are only indicative